## **EUROPEAN PATENT OFFICE**

## **Patent Abstracts of Japan**

**PUBLICATION NUMBER** 

61001060

**PUBLICATION DATE** 

07-01-86

**APPLICATION DATE** 

13-06-84

APPLICATION NUMBER

59124096

APPLICANT: MITSUBISHI ELECTRIC CORP;

INVENTOR: ANDO TORAHIKO;

INT.CL.

H01L 29/91 H01L 29/48 H01L 31/04

TITLE

MANUFACTURE OF MIS DIODE

ABSTRACT :

PURPOSE: To obtain high and stable performance by forming an insulating organic layer on a metal electrode by electrolytic polymerizing method, forming a semiconductor layer thereon, and further forming a conductive layer to become an electrode thereon.

CONSTITUTION: An Al electrode 14 is formed on a glass substrate 15 as an operating electrode. A poly  $\alpha$ -naphthole layer 12 is precipitated as an insulating organic polymer layer on the electrode to obtain an insulating organic polymer sample. A poly N-methylpyrrole film 11 is precipitated as a  $\pi$ -conjugate polymer layer on the sample, and an Au electrode 10 is formed on the film 11. A MIS diode having high performance and stable performance can be readily formed by the above manufacturing method.

COPYRIGHT: (C)1986,JPO&Japio

Best Available Copy